

Thermocouple combinations

Available Thermocouple Combinations

Combination	Type	Temperature Continuously		Temperature Intermittently	
		DEG F	DEG C	DEG F	DEG C
Platinum 10% Rhodium	S	2550	1400	3000	1650
Platinum 13% Rhodium	R	2550	1400	3000	1650
Pt 6% Rh v Pt 30 % Rh	B	2900	1600	3210	1770
Pt 20% Rh v Pt 40% Rh		2900	1800	3360	1850

